

इंटरनेट

मानक

Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan


“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”

IS 430 (1972): Paint remover, solvent type, non-flammable
[CHD 20: Paints, Varnishes and Related Products]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”

BLANK PAGE



IS : 430 - 1972
(Reaffirmed 2009)

Indian Standard
**SPECIFICATION FOR PAINT REMOVER,
SOLVENT TYPE, NON-FLAMMABLE**
(Second Revision)

Third Reprint AUGUST 2007
(Including Amendment No. 1)

UDC 667.691

© Copyright 1973
BUREAU OF INDIAN STANDARDS
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

AMENDMENT NO. 1 JUNE 1988
TO
IS : 430 - 1972 SPECIFICATION FOR PAINT
REMOVER, SOLVENT TYPE, NON-FLAMMABLE
(Second Revision)

(Page 5, clause 3.8, line 3) — Substitute '12 months' for '2 years'.

(CDC 8)

Indian Standard

SPECIFICATION FOR PAINT REMOVER, SOLVENT TYPE, NON-FLAMMABLE (*Second Revision*)

Paints and Allied Products Sectional Committee, CDC 8

<i>Chairman</i>	<i>Representing</i>
SHRI T. K. S. MANI	Addisons Paints and Chemicals Ltd, Madras
<i>Members</i>	
SHRI M. B. SATYANARAYANA (<i>Alternate to</i> Shri T. K. S. Mani)	
SHRI BALJIT SINGH	Bhagsons Paint Industries (India), New Delhi
SHRI HARDIP SINGH (<i>Alternate</i>)	
DR A. S. BHADURI	National Test House, Calcutta
SHRI K. C. SEAL (<i>Alternate</i>)	
SHRI P. K. BHANDARI	Shalimar Paints Ltd, Calcutta
SHRI C. J. BHUMKAR	Asian Paints (India) Pvt Ltd, Bombay
SHRI A. K. CAPRIHAN	Indian Aluminium Co Ltd, Calcutta
SHRI J. K. ANAND (<i>Alternate</i>)	
SHRI K. N. CHOWDHRI	Ministry of Defence (DGI)
SHRI S. K. MAITRA (<i>Alternate</i>)	
JOINT DIRECTOR (M & C)	Railway Board (Ministry of Railways)
SHRI A. RAMAMURTHY (<i>Alternate</i>)	
DR G. W. KAPSE	Central Building Research Institute (CSIR), Roorkee
DR S. M. SINGH (<i>Alternate</i>)	
SHRI R. K. MARPHATIA	Goodlass Nerolac Paints Ltd, Bombay
SHRI N. R. KOLWALKAR (<i>Alternate</i>)	
SHRI M. N. RAO	Indian Paint Association, Calcutta
SHRI B. V. DALAL (<i>Alternate</i>)	
SHRI R. K. ROKADE	The Premier Automobiles Ltd, Bombay
SHRI P. K. DESHPANDE (<i>Alternate</i>)	
SHRI G. S. SAVKAR	Directorate General of Supplies & Disposals, New Delhi
SCIENTIFIC ADVISOR TO THE CHIEF OF THE NAVAL STAFF	Naval Headquarters
SHRI N. K. SEN	Development Commissioner, Small Scale Industries, New Delhi
SHRI P. R. MALHAN (<i>Alternate</i>)	
SHRI K. N. R. SHARMA	Directorate General of Technical Development, New Delhi
SHRI S. N. AGARWAL (<i>Alternate</i>)	

(Continued on page 2)

BUREAU OF INDIAN STANDARDS
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

IS : 430 - 1972

(Continued from page 1)

<i>Members</i>		<i>Representing</i>
DR M. A. SIVASAMBAN		Regional Research Laboratory (CSIR), Hyderabad
SUPERINTENDING SURVEYOR OF WORKS (I)		Central Public Works Department, New Delhi
SURVEYOR OF WORKS (I) (<i>Alternate</i>)		
SHRI Y. S. SWAMY		The Alkali & Chemical Corporation of India Ltd, Calcutta
SHRI S. BHATTACHARYYA (<i>Alternate</i>)		
SHRI D. DAS GUPTA,		Director General, ISI (<i>Ex-officio Member</i>)
Director (Chem)		
		<i>Secretary</i>
		SHRI R. K. SINGH
		Assistant Director (Chem), ISI

Fanel for RMP's, Enamels and Adjuncts, CDC 8:6:6

<i>Convener</i>	
DR P. K. BHANDRI	Shalimar Paints Ltd, Calcutta
<i>Members</i>	
SHRI S. K. ASTHANA	Ministry of Defence (DGI)
JOINT DIRECTOR (M & C)	Railway Board (Ministry of Railways)
SHRI T. K. S. MANI	Addisons Paints and Chemicals Ltd, Madras
SHRI M. N. RAO	Indian Paint Association, Calcutta
DR A. B. GERSAPPE (<i>Alternate</i>)	

Indian Standard
**SPECIFICATION FOR PAINT REMOVER,
SOLVENT TYPE, NON-FLAMMABLE**
(*Second Revision*)

0. FOREWORD

0.1 This Indian Standard (Second Revision) was adopted by the Indian Standards Institution on 15 September 1972, after the draft finalized by the Paints and Allied Products Sectional Committee had been approved by the Chemical Division Council.

0.2 This standard was originally issued in 1953 and subsequently revised in 1964. The original revision of this standard was based on the interim co-ordinated draft prepared by the Co-ordinating Subcommittee of the No. 5 Standing Committee on Specifications for Paints and Allied Stores of the General Headquarters (now Army Headquarters), India. In this revision an additional requirement for consistency and a method for its determination has been included and requirements for nonvolatile matter have been modified.

0.3 This standard achieves alignment with JSS 3074 'Specification for paint remover non-inflammable', issued by the Department of Standardization, Ministry of Defence, Government of India.

0.4 This standard is one of the two Indian Standard specifications on paint removers. The other Indian Standard specification is IS: 431-1972*.

0.5 For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis; shall be rounded off in accordance with IS : 2-1960†. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

1. SCOPE

1.1 This standard prescribes requirements and methods of sampling and test for the material commercially known as paint remover, solvent type, non-flammable.

*Specification for paint remover, solvent type, flammable (*second revision*).

†Rules for rounding off numerical values (*revised*).

IS : 430 - 1971

1.1.1 The material is intended for general use on vertical and horizontal surfaces of painted, varnished or lacquered wood, plaster and metal. Certain types of coatings, such as some-stoving cold-cured or polymeric materials may not be readily acted upon by the material covered by this specification.

2. TERMINOLOGY

2.1 For the purpose of this standard, the definitions given in IS : 1303-1963* and in 2 of IS : 101-1964† shall apply.

3. REQUIREMENTS

3.1 Form and Condition — The material shall be a homogeneous liquid and shall be free from grit and other visible impurities.

3.2 Composition — The material shall be of such a composition as to comply with the requirements of this standard.

3.3 Freedom from Alkalinity and Acidity — When tested as prescribed in Appendix A, the water extract prepared from the material shall not give red colour with phenolphthalein and blue colour with congo red, when added to portions of the water extract separately.

3.4 Non-volatile Matter — When tested as prescribed in Appendix B, the material shall have a residue between 4 and 10 percent by mass.

3.5 Consistency — The material when tested as prescribed in Appendix C shall have a rate of flow similar to that of an oil of viscosity not lower than 10 P and not higher than 20 P.

3.6 Efficiency — When applied by a brush or a swab to a thoroughly dry, old (air-dried or stoved) paint film and allowed to stand for 5 minutes, the material shall soften the paint film to such an extent that it is easily removed with a scraper made of wood or non-ferrous metal. In this respect, the material, when tested at the same time and in the same manner, shall not be inferior in efficiency to either of the mixtures of the following compositions.

Composition 1

a) Dichloromethane	90 ml
b) Ordinary denatured spirit conforming to IS : 324-1959‡	10 ml
c) Cellulose acetate, medium viscosity	10 g
d) Paraffin wax	1.5 g

*Glossary of terms relating to paints (*revised*).

†Methods of test for ready mixed paints and enamels (*second revision*).

‡Specification for ordinary denatured spirit (*revised*).

Composition 2

a) Dichloromethane	70 g
b) Trichloroethylene conforming to IS: 245-1970*	26 g
c) Paraffin wax	4 g

3.7 Non-flammability — The material shall not support combustion when a burning match stick is applied for 5 seconds to the edge of a piece of linen cloth (approximately 100×50 mm) dipped into the material, the cloth after dipping being allowed to drain for 5 minutes.

3.8 Keeping Properties — When stored in original sealed containers under normal temperature conditions, the material shall satisfy, for a period of not less than 2 years from the date of manufacture, the requirements prescribed in this standard.

4. PACKING AND MARKING

4.1 Packing — The material shall be suitably packed in well-closed containers. The packing shall be as agreed to between the purchaser and the supplier and subject to the provisions of the law in force in the country at the time of packing.

4.1.1 All containers in which the material is stored shall be clean, dry and leak-proof. The containers shall be protected from light and stored preferably in a cool and dry place. If the containers are closed with corks, the latter shall be protected with metal foil.

4.2 Marking — Each container shall be marked with the following;

- a) Name of the material;
- b) Name of the manufacturer and/or trade-mark, if any;
- c) Volume of the material; and
- d) Month and year of manufacture.

4.2.1 The product may also be marked with Standard Mark.

4.2.2 The use of the Standard Mark is governed by the provisions of the Bureau of Indian Standards Act, 1986 and the Rules and Regulations made thereunder. The details of conditions under which the licence for the use of Standard Mark may be granted to manufacturers or producers may be obtained from the Bureau of Indian Standards.

*Specification for trichloroethylene, technical (*second revision*).

IS : 430 - 1972

4.3 The material, when intended for defence purposes, shall be packed and marked in accordance with IS : 5661-1970*.

5. SAMPLING

5.1 Representative samples of the material shall be drawn as prescribed in 3 of IS: 101-1964†.

6. TEST METHODS

6.1 Tests shall be conducted as prescribed in appendices to this standard. References to relevant appendices are given in **3.3** to **3.5**.

6.2 Quality of Reagents — Unless otherwise specified, pure chemicals and distilled water (see IS : 1070-1960‡) shall be employed in tests.

NOTE — 'Pure chemicals' shall mean chemicals that do not contain impurities which affect the results of analysis.

7. CRITERIA FOR CONFORMITY

7.1 A lot shall be declared as conforming to the requirements of this standard, if the test results of composite sample satisfy the requirements prescribed under 3.

APPENDIX A

(Clause 3.3)

TEST FOR FREEDOM FROM ALKALINITY AND ACIDITY

A 1. REAGENTS

A-1.1 Phenolphthalein Indicator — Dissolve 0.1 g of phenolphthalein in 100 ml of 60 percent rectified spirit.

A-1.2 Congo Red Indicator — Dissolve 0.1 g of congo red in 10 ml of rectified spirit conforming to IS : 323-1959§ and dilute to 100 ml with water.

A-2. Procedure

A-2.1 Prepare a water extract of the material by shaking it with twice its volume of freshly boiled and cooled water. Test the freedom from alkalinity and acidity by adding phenolphthalein indicator and congo red indicator to separate portions of the extracts.

*Code of practice for packing and marking of packages of paints, enamels, varnishes and allied products.

†Methods of test for ready mixed paints and enamels (*second revision*).

‡Specification for water, distilled quality (*revised*).

§Specification for rectified spirit (*revised*).

APPENDIX B

(Clause 3.4)

DETERMINATION OF NONVOLATILE MATTER

B-1. PROCEDURE

B-1.1 Weigh accurately about 4 g of the material by difference from a stoppered tube in a previously weighed flat-bottomed dish, 75 mm in diameter. Keep the dish on a water-bath for 1 hour and then place it in an air-oven maintained at 105 to 110°C for about 30 minutes. Cool it in a desiccator and weigh. Repeat the heating, cooling and weighing till a constant mass is obtained.

B-1.2 Report the residue as percentage of the mass of the material taken for the test.

APPENDIX C

(Clause 3.5)

DETERMINATION OF CONSISTENCY

C-0. GENERAL

C-0 1 Outline of the Method – The viscosity of the material is determined by measuring the force required to impart a certain speed to a cylinder immersed in the material.

C-1. APPARATUS

C-1.1 Viscometer— Stormer viscometer with the paddle type rotor, as illustrated in Fig. 1 and 2. Intercalibration of any two viscometers may be carried out by determining the load in grams required to produce a shearing rate of 200 rev/min with a standard oil having a viscosity of 10 to 20 P at 25°C.

C-1.2 Container— 150-ml friction-top can, 8.6 cm in diameter.

C-1.3 Thermometer— a suitable thermometer having a range of 20 to 70°C.

C-2. PROCEDURE

C-2.1 Pour the material into the container and fill to three-fourths. Bring the temperature of the sample to $25 \pm 0.2^\circ\text{C}$ and maintain at that

IS : 430 - 1972

temperature during test. Set the container on the stand of the viscometer and raise to the level of the mark on the paddle shaft. Connect the lamp circuit to ac mains. Before starting the test, turn the rotor through approximately 100 revolutions in 25 to 30 seconds. Using different masses, determine to the nearest 5 g the mass necessary to produce 200 rev/min pattern (see Note) on the stroboscopic timer where the lines appear to remain stationary. Lines moving in the direction of rotation of the paddle indicate a speed greater than 200 rev/min and the mass shall be removed. Conversely, lines moving opposite to direction of rotation of the paddle indicate a speed less than 200 rev/min and the mass shall be added. Repeat the test until consistent results are obtained.

NOTE — There are other patterns which appear at speeds other than 200 rev/min. The pattern for 200 rev/min should be determined before running any tests.

C-2.2 Report the consistency of the material in terms of mass in grams necessary to produce the 200 rev/min pattern.





FIG. 1 STORMER VISCOMETER WITH PADDLE TYPE ROTOR AND STROBOSCOPIC TIMER



All dimensions in millimetres.

FIG. 2 PADDLE TYPE ROTOR FOR USE WITH STORMER VISCOMETER

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan 9 Bahadur Shah Zafar Marg, NEW DELHI 110002
 Telephones 23230131, 23233375, 23239402 Fax 91+011 23239399, 23239382
 E - Mail info@bis org in website http://www.bis.org.in

Central Laboratory:

Plot No 20/9 Site IV Sahibabad Industrial Area, SAHIBABAD 201010

Telephone

277 0032

Regional Offices:

Central	Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002	2323 7617
*Eastern	1/14 CIT Scheme VII M, V I P Road, Kankurgachi, KOLKATA 700054	2337 8662
Northern	SCO 335-336, Sector 34-A, CHANDIGARH 160022	260 9285
Southern	C I T Campus, IV Cross Road, CHENNAI 600113	2254 1984
†Western	Manakalaya, E9 MIDC, Behind Marol Telephone Exchange, Andheri (East), MUMBAI 400093	2832 9295

Branch Offices:

'Pushpak',	Nurmohamed Shaikh Marg, Khanpur, AHMEDABAD 380001	560 1348
Peenya Industrial Area, 1 st Stage,	Bangalore-Tumkur Road, BANGALORE	839 4955
Commercial-cum-Office Complex, Opp	Dushera Maidan, Arera Colony, Bittan Market, BHOPAL 462016	242 3452
62-63, Ganga Nagar, Unit VI,	BHUBANESHWAR 751001	240 3139
5 th Floor, Kovai Towers, 44 Bala Sundaram Road,	COIMBATORE 641018	221 0141
SCO 21, Sector 12, Faridabad	121007	229 2175
Savitri Complex, 116 G T Road,	GHAZIABAD 201001	286 1498
53/5 Ward No 29, R G Barua Road, 5th By-lane,	Apurba Sinha Path, GUWAHATI 781003	245 6508
5-8-56C, L N Gupta Marg, Nampally Station Road,	HYDERABAD 500001	2320 1084
Prithavi Raj Road, Opposite Bharat Overseas Bank, C-Scheme,	JAIPUR 302001	222 3282
11/418 B, Sarvodaya Nagar,	KANPUR 208005	223 3012
Sethi Bhawan, 2 nd Floor, Behind Leela Cinema, Naval Kishore Road,	LUCKNOW 226001	261 8923
H No 15, Sector-3, PARWANOO, Distt Solan (H P)	173220	235 436
Plot No A-20-21, Institutional Area, Sector 62, Goutam Budh Nagar,	NOIDA 201307	240 2206
Patliputra Industrial Estate,	PATNA 800013	226 2808
Plot Nos 657-660, Market Yard, Gultkdi,	PUNE 411037	2427 4804
"Sahajanand House" 3 rd Floor, Bhaktinagar Circle, 80 Feet Road,	RAJKOT 360002	237 8251
T C No 2/275 (1 & 2), Near Food Corporation of India, Kesavadasapuram-Ulloor Road,	Kesavadasapuram, THIRUVANANTHAPURAM 695004	255 7914
1 st Floor, Udyog Bhavan, VUDA, Siripuram Junction,	VISHAKHAPATNAM-03	271 2833
*Sales Office is at 5 Chowringhee Approach, P O Princep Street,	KOLKATA 700072	2355 3243
†Sales Office (WRO) Plot No E-9, MIDC, Rd No 8, Behind Telephone Exchange,	Andheri (East), Mumbai-400 0093	2832 9295